


←out

Serge 600

COLLECTION 2018-2021
REFLECTS SUNLIGHT OUTDOORS
GLASSFIBRE
OF = 5%



**Screens that
reflect & absorb
solar energy
outside the house.
Meet OUT.**





Serge 600



GLASSFIBRE

OF = 5%

Technical specifications

| TECHNICAL SPECIFICATION | | UNITY | | STANDARD | RESULT |
|--|--|---------------------|------|--------------------------|---------|
| composition | | | | Glassfibre 42% - PVC 58% | |
| openness factor | | % | | NBN EN 410 | 5% |
| weight | | g/m ² | | NF EN 12127 | 525 |
| thickness | | mm | | ISO 2286-3 | 0,74 |
| density | | yarn/cm | warp | ISO 7211/2 | 18 |
| | | | weft | | 14 |
| colour fastness to artificial light | | | | ISO 105 B02 | >7 |
| colour fastness to artificial weathering | | | | ISO 105 B04 | >7 |
| tear strength | original | daN | warp | ISO 4674-1 method 2 | 8,5 |
| | | | weft | | 7,5 |
| elongation up to break | original | % | warp | ISO 1421 | 3,1 |
| | | | weft | | 2,75 |
| breaking strength | original | daN/5 cm | warp | ISO 1421 | 260 |
| | | | weft | | 225 |
| elongation up to break | after colour fastness to artificial weathering | % | warp | ISO 1421 | 3,5 |
| | | | weft | | 2,8 |
| breaking strength | after colour fastness to artificial weathering | % | warp | ISO 1421 | 240 |
| | | | weft | | 225 |
| elongation up to break | after colour fastness to artificial light | % | warp | ISO 1421 | 4 |
| | | | weft | | 2,9 |
| breaking strength | after colour fastness to artificial light | daN/5 cm | warp | ISO 1421 | 240 |
| | | | weft | | 220 |
| tear strength | after climatic chamber -30°C | daN | warp | ISO 4674-1 method 2 | 7,8 |
| | | | weft | | 7,5 |
| elongation up to break | after climatic chamber -30°C | % | warp | ISO 1421 | 3 |
| | | | weft | | 2,5 |
| breaking strength | after climatic chamber -30°C | daN/5 cm | warp | ISO 1421 | 225 |
| | | | weft | | 200 |
| tear strength | after climatic chamber +70°C | daN | warp | ISO 4674-1 method 2 | 8,2 |
| | | | weft | | 7,2 |
| elongation up to break | after climatic chamber +70°C | % | warp | ISO 1421 | 2,85 |
| | | | weft | | 2,5 |
| breaking strength | after climatic chamber +70°C | daN/5 cm | warp | ISO 1421 | 180 |
| | | | weft | | 185 |
| air permeability | | l/m ² .s | | ISO 9237 | 580 |
| fire classification | Europe | | | UNE-EN 13501-1:2007 | C-s3,d0 |
| | France | | | NF P92-503 | M1 |
| | Italy | | | UNI 9177 | Class 1 |
| | Germany | | | DIN 4102 | B1 |
| | UK | | | BS 5867 | C |
| | USA | | | NFPA 701 | FR |
| roll length | 50 m / 30 m for all widths > 270 cm | | | | |
| cleaning | with soapy water | | | | |
| confection | by heat, high frequency or ultrasonic welding | | | | |

These properties are given as indicative and don't have any contractual value

Serge 600 010010 charcoal | charcoal






Serge 600



GLASSFIBRE

OF = 5%


Colours & references




Serge 600 002002 white | white




Serge 600 008002 linen | white




Serge 600 008008 linen | linen



Serge 600 033033 sandstone



Serge 600 001003 grey | sand



Serge 600 003011 sand | bronze




Serge 600 003003 sand | sand




Serge 600 003002 sand | white




Serge 600 002007 white | pearl grey




Serge 600 008016 linen | bordeaux




Serge 600 002061 white | white-pearl grey




Serge 600 007002 pearl grey | white



Serge 600 008007 linen | pearl grey




Serge 600 007082 pearl grey | white-sand




Serge 600 008003 linen | sand



Serge 600 001002 grey | white



Serge 600 007007 pearl grey | pearl grey



Serge 600 033001 oyster shell






Serge 600



GLASSFIBRE

OF = 5%


Colours & references




Serge 600 031031 jade river




Serge 600 032031 duck egg




Serge 600 032032 wet sand




Serge 600 033041 maroon




Serge 600 001045 coconut




Serge 600 008015 linen | lichen




Serge 600 033032 soft clay




Serge 600 001006 grey | yellow




Serge 600 001004 grey | gold




Serge 600 008001 safari




Serge 600 001074 grey | yellow-green




Serge 600 001012 grey | green




Serge 600 008079 linen | grey-gold




Serge 600 032040 mango




Serge 600 001005 grey | mandarin



Serge 600 033043 moss



Serge 600 001044 palm



Serge 600 001014 grey | turquoise




Serge 600




GLASSFIBRE

OF = 5%


Colours & references



Serge 600 007009 pearl grey | blue azure




Serge 600 001070 grey | pearl grey-blue azure



Serge 600 001009 grey | blue azure




Serge 600 030030 pure black | pure black



Serge 600 001094 lagoon




Serge 600 001042 shade




Serge 600 001001 grey | grey




Serge 600 011011 bronze | bronze



Serge 600 001061 grey | white-pearl grey



Serge 600 001010 grey | charcoal



Serge 600 010010 charcoal | charcoal



Serge 600 010011 charcoal | bronze

| Serge 600 | | 50 m roll | | | | | 30 m roll | |
|------------------------------|--------|-----------|--------|--------|--------|--------|-----------|--------|
| | | 160 cm | 190 cm | 220 cm | 250 cm | 270 cm | 320 cm | 350 cm |
| colour | code | | | | | | | |
| grey / grey | 001001 | • | • | • | • | • | • | • |
| grey / white | 001002 | • | • | • | • | • | • | • |
| grey / sand | 001003 | • | • | • | • | • | • | |
| grey / gold | 001004 | • | • | • | • | • | • | |
| grey / mandarin | 001005 | • | • | • | • | • | • | |
| grey / yellow | 001006 | • | • | • | • | • | • | |
| grey / blue azure | 001009 | • | • | • | • | • | • | |
| grey / charcoal | 001010 | • | • | • | • | • | • | • |
| grey / green | 001012 | • | • | • | • | • | • | |
| grey / turquoise | 001014 | • | • | • | • | • | • | |
| shade | 001042 | | | • | | • | • | |
| palm | 001044 | | | • | | • | • | |
| coconut | 001045 | | | • | | • | • | |
| grey / white-pearl grey | 001061 | • | • | • | • | • | • | |
| grey / pearl grey-blue azure | 001070 | • | • | • | • | • | • | |
| grey / yellow-green | 001074 | • | • | • | • | • | • | |
| lagoon | 001094 | | | • | | • | • | |
| white/white | 002002 | | • | • | • | • | • | • |
| white/pearl grey | 002007 | | • | • | • | • | • | |
| white/white-pearl grey | 002061 | | | • | • | • | • | |
| sand/white | 003002 | | | • | • | • | • | |
| sand/sand | 003003 | | | • | • | • | • | |

Serge 600



GLASSFIBRE

OF = 5%

| Serge 600 | | 50 m roll | | | | | 30 m roll | |
|-------------------------|--------|-----------|--------|--------|--------|--------|-----------|--------|
| | | 160 cm | 190 cm | 220 cm | 250 cm | 270 cm | 320 cm | 350 cm |
| colour | code | | | | | | | |
| sand / bronze | 003011 | | | • | • | • | • | |
| pearl grey / white | 007002 | | | • | • | • | • | |
| pearl grey / pearl grey | 007007 | | • | • | • | • | • | • |
| pearl grey / blue azure | 007009 | | | • | • | • | • | |
| pearl grey / white-sand | 007082 | | | | • | • | • | |
| linen/white | 008002 | | • | • | • | • | • | |
| linen / sand | 008003 | | | | • | • | • | |
| linen / pearl grey | 008007 | | | | • | • | • | |
| linen/linen | 008008 | | • | • | • | • | • | |
| linen / lichen | 008015 | | | | • | • | • | |
| linen / bordeaux | 008016 | | | | • | • | • | |
| linen / grey-gold | 008079 | | | | • | • | • | |
| safari | 008001 | | | • | • | • | • | |
| charcoal / charcoal | 010010 | • | • | • | • | • | • | • |
| pure black / pure black | 010010 | | | | | • | • | |
| charcoal / bronze | 010011 | | • | • | • | • | • | |
| bronze / bronze | 011011 | | • | • | • | • | • | |
| jade river | 031031 | | | • | • | • | • | |
| duck egg | 032031 | | | • | • | • | • | |
| wet sand | 032032 | | | • | • | • | • | |
| mango | 032040 | | | • | • | • | • | |
| oyster shell | 033001 | | | • | • | • | • | |
| soft clay | 033032 | | | • | • | • | • | |
| sandstone | 033033 | | | • | • | • | • | |
| maroon | 033041 | | | • | • | • | • | |
| moss | 033043 | | | • | • | • | • | |

Solar energetic properties

| Serge 600 European Standard EN 14501 Calculation G-value according to EN 13363-1 version 7.0 | | SOLAR ENERGETIC PROPERTIES | | | | | | | | | | | | | | VISUAL PROPERTIES | |
|--|-------------------------|---|------|-------------------------|--------------------------|----------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|------------------------------------|--------------------------|---------------------------------|---------------------------------|------|
| | | FABRIC | | | FABRIC + GLAZING | | | | | | | | | | | | |
| | | | | | EXTERIOR | | | | | INTERIOR | | | | | | | |
| | | G-factor = total solar energy transmittance | | | | | | | | | | | Tv = Visible Light Transmittance % | Tuv = UV Transmittance % | | | |
| references | colours | front | back | As = Solar Absorbance % | Rs = Solar Reflectance % | Ts = Solar Transmittance % | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | | | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | |
| | | | | | | | 002002 | white white | front | back | front | 13,2 | 65,9 | 21,0 | 0,22 | 0,20 | 0,15 |
| back | 12,7 | 66,3 | 21,0 | 0,22 | 0,19 | 0,15 | | | 0,10 | 0,35 | 0,37 | 0,36 | 0,25 | 21,2 | 4,3 | | |
| 008002 | linen white | front | back | front | 26,4 | 58,2 | 15,5 | 0,20 | 0,17 | 0,13 | 0,09 | 0,39 | 0,41 | 0,38 | 0,26 | 13,7 | 5,3 |
| | | back | 28,1 | 56,4 | 15,5 | 0,20 | 0,17 | 0,13 | 0,09 | 0,40 | 0,42 | 0,39 | 0,26 | 13,7 | 5,3 | | |
| 008008 | linen linen | front | back | front | 32,5 | 52,5 | 14,9 | 0,21 | 0,17 | 0,13 | 0,09 | 0,43 | 0,43 | 0,40 | 0,26 | 12,9 | 5,8 |
| | | back | 32,4 | 52,7 | 14,9 | 0,20 | 0,17 | 0,13 | 0,09 | 0,42 | 0,43 | 0,40 | 0,26 | 12,9 | 5,8 | | |
| 003003 | sand sand | front | back | front | 54,1 | 36,5 | 9,4 | 0,20 | 0,16 | 0,11 | 0,09 | 0,51 | 0,51 | 0,45 | 0,28 | 7,7 | 4,9 |
| | | back | 53,6 | 37,0 | 9,4 | 0,20 | 0,16 | 0,11 | 0,08 | 0,51 | 0,51 | 0,45 | 0,28 | 7,7 | 4,9 | | |
| 003002 | sand white | front | back | front | 39,1 | 49,2 | 11,7 | 0,19 | 0,16 | 0,11 | 0,08 | 0,44 | 0,45 | 0,41 | 0,27 | 10,2 | 4,9 |
| | | back | 43,6 | 44,6 | 11,7 | 0,20 | 0,17 | 0,12 | 0,09 | 0,47 | 0,47 | 0,42 | 0,27 | 10,2 | 4,9 | | |
| 002007 | white pearl grey | front | back | front | 40,9 | 47,6 | 11,5 | 0,19 | 0,16 | 0,11 | 0,08 | 0,45 | 0,46 | 0,42 | 0,27 | 10,7 | 6,0 |
| | | back | 33,2 | 55,3 | 11,5 | 0,18 | 0,15 | 0,11 | 0,08 | 0,40 | 0,42 | 0,39 | 0,26 | 10,7 | 6,0 | | |
| 008007 | linen pearl grey | front | back | front | 45,7 | 43,5 | 10,8 | 0,20 | 0,16 | 0,11 | 0,08 | 0,47 | 0,48 | 0,43 | 0,27 | 9,1 | 5,0 |
| | | back | 42,1 | 47,1 | 10,8 | 0,19 | 0,16 | 0,11 | 0,08 | 0,45 | 0,46 | 0,42 | 0,27 | 9,1 | 5,0 | | |
| 007082 | pearl grey white-sand | front | back | front | 48,7 | 42,6 | 8,7 | 0,18 | 0,15 | 0,10 | 0,08 | 0,48 | 0,48 | 0,43 | 0,27 | 7,8 | 6,1 |
| | | back | 52,4 | 38,9 | 8,7 | 0,19 | 0,15 | 0,10 | 0,08 | 0,50 | 0,50 | 0,44 | 0,27 | 7,8 | 6,1 | | |
| 008003 | linen sand | front | back | front | 49,3 | 43,9 | 6,8 | 0,17 | 0,13 | 0,09 | 0,07 | 0,46 | 0,47 | 0,43 | 0,27 | 4,9 | 2,0 |
| | | back | 44,9 | 48,3 | 6,8 | 0,16 | 0,13 | 0,08 | 0,07 | 0,44 | 0,45 | 0,41 | 0,27 | 4,9 | 2,0 | | |

| | |
|--|-----------|
| GLAZING A = clear single glazing 4 mm | Gv = 0,85 |
| GLAZING B = clear double glazing (4/12/4), space filled with air | Gv = 0,76 |
| GLAZING C = double glazing (4/16/4), with a low emissivity coating in position 3, space filled with argon | Gv = 0,59 |
| GLAZING D = reflective double glazing (4/16/4), with a low emissivity coating in position 2, space filled with argon | Gv = 0,32 |



Serge 600



GLASSFIBRE

OF = 5%

Solar energetic properties

| Serge 600 European Standard EN 14501 Calculation G-value according to EN 13363-1 version 7.0 | | SOLAR ENERGETIC PROPERTIES | | | | | | | | | | | | | | VISUAL PROPERTIES | |
|--|--------------------------|----------------------------|--------------------------|---|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|------------------------------------|--------------------------|-------|-------------------|--|
| | | FABRIC | | FABRIC + GLAZING | | | | | | | | | | | | | |
| | | | | EXTERIOR | | | | | | INTERIOR | | | | | | | |
| | | | | G-factor = total solar energy transmittance | | | | | | | | | | | | | |
| references | colours | As = Solar Absorbance % | Rs = Solar Reflectance % | Ts = Solar Transmittance % | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Tv = Visible Light Transmittance % | Tuv = UV Transmittance % | | | |
| | | | | | | | | | | | | | | | front | back | |
| 033033 | sandstone | front | 72,4 | 20,5 | 7,1 | 0,22 | 0,17 | 0,11 | 0,09 | 0,60 | 0,59 | 0,50 | 0,29 | 6,8 | 6,6 | | |
| | | back | 72,5 | 20,4 | 7,1 | 0,22 | 0,17 | 0,11 | 0,09 | 0,60 | 0,59 | 0,50 | 0,29 | 6,8 | 6,6 | | |
| 001003 | grey sand | front | 68,8 | 26,5 | 4,7 | 0,19 | 0,15 | 0,09 | 0,08 | 0,56 | 0,56 | 0,48 | 0,29 | 4,5 | 3,9 | | |
| | | back | 73,8 | 21,5 | 4,7 | 0,20 | 0,15 | 0,10 | 0,08 | 0,59 | 0,59 | 0,50 | 0,29 | 4,5 | 3,9 | | |
| 003011 | sand bronze | front | 73,2 | 21,1 | 5,7 | 0,21 | 0,16 | 0,10 | 0,09 | 0,60 | 0,59 | 0,50 | 0,29 | 5,0 | 4,0 | | |
| | | back | 66,3 | 28,0 | 5,7 | 0,19 | 0,15 | 0,10 | 0,08 | 0,56 | 0,55 | 0,48 | 0,28 | 5,0 | 4,0 | | |
| 008016 | linen bordeaux | front | 63,4 | 26,1 | 10,5 | 0,23 | 0,19 | 0,13 | 0,01 | 0,57 | 0,57 | 0,48 | 0,29 | 8,4 | 4,2 | | |
| | | back | 54,3 | 35,3 | 10,5 | 0,21 | 0,17 | 0,12 | 0,09 | 0,52 | 0,52 | 0,45 | 0,28 | 8,4 | 4,2 | | |
| 002061 | white white-pearl grey | front | 27,7 | 59,8 | 12,4 | 0,17 | 0,15 | 0,11 | 0,08 | 0,38 | 0,40 | 0,38 | 0,26 | 11,6 | 3,4 | | |
| | | back | 23,4 | 64,2 | 12,4 | 0,16 | 0,14 | 0,10 | 0,07 | 0,35 | 0,37 | 0,36 | 0,25 | 11,6 | 3,4 | | |
| 007002 | pearl grey white | front | 37,4 | 50,9 | 11,7 | 0,19 | 0,16 | 0,11 | 0,08 | 0,43 | 0,44 | 0,40 | 0,26 | 9,9 | 5,4 | | |
| | | back | 41,4 | 46,9 | 11,7 | 0,19 | 0,16 | 0,11 | 0,08 | 0,45 | 0,46 | 0,42 | 0,27 | 9,9 | 5,4 | | |
| 001002 | grey white | front | 56,2 | 37,2 | 6,7 | 0,18 | 0,14 | 0,09 | 0,08 | 0,50 | 0,51 | 0,45 | 0,28 | 6,6 | 5,5 | | |
| | | back | 66,4 | 26,9 | 6,7 | 0,20 | 0,16 | 0,10 | 0,08 | 0,56 | 0,56 | 0,48 | 0,28 | 6,6 | 5,5 | | |
| 007007 | pearl grey pearl grey | front | 51,7 | 38,3 | 10,1 | 0,20 | 0,16 | 0,11 | 0,09 | 0,50 | 0,50 | 0,44 | 0,27 | 8,4 | 6,0 | | |
| | | back | 50,5 | 39,4 | 10,1 | 0,20 | 0,16 | 0,11 | 0,09 | 0,50 | 0,50 | 0,44 | 0,27 | 8,4 | 6,0 | | |
| 033001 | oyster shell | front | 74,7 | 17,0 | 8,3 | 0,23 | 0,19 | 0,12 | 0,10 | 0,62 | 0,61 | 0,51 | 0,29 | 8,0 | 7,9 | | |
| | | back | 73,3 | 18,4 | 8,3 | 0,23 | 0,18 | 0,12 | 0,10 | 0,62 | 0,60 | 0,51 | 0,29 | 8,0 | 7,9 | | |
| 031031 | jade river | front | 75,0 | 17,9 | 7,1 | 0,22 | 0,18 | 0,11 | 0,09 | 0,62 | 0,61 | 0,51 | 0,29 | 7,0 | 6,8 | | |
| | | back | 75,0 | 17,9 | 7,1 | 0,22 | 0,18 | 0,11 | 0,09 | 0,62 | 0,61 | 0,51 | 0,29 | 7,0 | 6,8 | | |

Solar energetic properties

| Serge 600 European Standard EN 14501 Calculation G-value according to EN 13363-1+A1: 2007 | | SOLAR ENERGETIC PROPERTIES | | | | | | | | | | | | | | VISUAL PROPERTIES | |
|---|-------------------|----------------------------|--------------------------|---|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|------------------------------------|--------------------------|-------|-------------------|--|
| | | FABRIC | | FABRIC + GLAZING | | | | | | | | | | | | | |
| | | | | EXTERIOR | | | | | | INTERIOR | | | | | | | |
| | | | | G-factor = total solar energy transmittance | | | | | | | | | | | | | |
| references | colours | As = Solar Absorbance % | Rs = Solar Reflectance % | Ts = Solar Transmittance % | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Tv = Visible Light Transmittance % | Tuv = UV Transmittance % | | | |
| | | | | | | | | | | | | | | | front | back | |
| 032031 | duck egg | front | 70,4 | 22,5 | 7,1 | 0,21 | 0,17 | 0,11 | 0,09 | 0,59 | 0,58 | 0,50 | 0,29 | 6,6 | 6,2 | | |
| | | back | 67,6 | 25,3 | 7,1 | 0,21 | 0,16 | 0,11 | 0,09 | 0,57 | 0,57 | 0,49 | 0,29 | 6,6 | 6,2 | | |
| 032032 | wet sand | front | 63,8 | 27,9 | 8,3 | 0,21 | 0,17 | 0,11 | 0,09 | 0,56 | 0,56 | 0,48 | 0,28 | 7,4 | 6,9 | | |
| | | back | 63,8 | 27,9 | 8,3 | 0,21 | 0,17 | 0,11 | 0,09 | 0,56 | 0,56 | 0,48 | 0,28 | 7,4 | 6,9 | | |
| 033032 | soft clay | front | 67,5 | 24,7 | 7,8 | 0,21 | 0,17 | 0,11 | 0,09 | 0,58 | 0,57 | 0,49 | 0,29 | 7,3 | 7,0 | | |
| | | back | 69,7 | 22,5 | 7,8 | 0,22 | 0,17 | 0,11 | 0,09 | 0,59 | 0,58 | 0,50 | 0,29 | 7,3 | 7,0 | | |
| 001006 | grey yellow | front | 64,6 | 29,0 | 6,4 | 0,20 | 0,15 | 0,10 | 0,08 | 0,55 | 0,55 | 0,47 | 0,28 | 6,2 | 4,4 | | |
| | | back | 71,4 | 22,2 | 6,4 | 0,21 | 0,16 | 0,11 | 0,09 | 0,59 | 0,58 | 0,50 | 0,29 | 6,2 | 4,4 | | |
| 001004 | grey gold | front | 65,5 | 29,5 | 4,9 | 0,18 | 0,14 | 0,09 | 0,08 | 0,55 | 0,55 | 0,47 | 0,28 | 4,3 | 3,7 | | |
| | | back | 72,3 | 22,8 | 4,9 | 0,20 | 0,15 | 0,10 | 0,08 | 0,59 | 0,58 | 0,49 | 0,29 | 4,3 | 3,7 | | |
| 008079 | linen grey-gold | front | 50,0 | 38,8 | 11,2 | 0,21 | 0,17 | 0,12 | 0,09 | 0,50 | 0,50 | 0,44 | 0,27 | 9,1 | 6,6 | | |
| | | back | 45,6 | 43,2 | 11,2 | 0,20 | 0,16 | 0,11 | 0,09 | 0,48 | 0,48 | 0,43 | 0,27 | 9,1 | 6,6 | | |
| 032040 | mango | front | 56,8 | 34,2 | 9,0 | 0,20 | 0,16 | 0,11 | 0,09 | 0,52 | 0,52 | 0,46 | 0,28 | 6,8 | 5,9 | | |
| | | back | 59,6 | 31,4 | 9,0 | 0,20 | 0,16 | 0,11 | 0,09 | 0,52 | 0,52 | 0,46 | 0,28 | 6,8 | 5,9 | | |
| 001005 | grey mandarine | front | 65,6 | 27,7 | 6,8 | 0,20 | 0,16 | 0,10 | 0,08 | 0,56 | 0,56 | 0,48 | 0,28 | 5,7 | 5,1 | | |
| | | back | 71,5 | 21,7 | 6,8 | 0,21 | 0,17 | 0,11 | 0,09 | 0,59 | 0,59 | 0,50 | 0,29 | 5,7 | 5,1 | | |
| 033041 | maroon | front | 66,5 | 25,9 | 7,6 | 0,21 | 0,17 | 0,11 | 0,09 | 0,57 | 0,57 | 0,48 | 0,29 | 6,4 | 6,2 | | |
| | | back | 69,6 | 22,8 | 7,6 | 0,21 | 0,17 | 0,11 | 0,09 | 0,57 | 0,57 | 0,48 | 0,29 | 6,4 | 6,2 | | |

| | |
|--|-----------|
| GLAZING A = clear single glazing 4 mm | Gv = 0,85 |
| GLAZING B = clear double glazing (4/12/4), space filled with air | Gv = 0,76 |
| GLAZING C = double glazing (4/16/4), with a low emissivity coating in position 3, space filled with argon | Gv = 0,59 |
| GLAZING D = reflective double glazing (4/16/4), with a low emissivity coating in position 2, space filled with argon | Gv = 0,32 |



Serge 600



GLASSFIBRE

OF = 5%

Solar energetic properties

| Serge 600 European Standard EN 14501 Calculation G-value according to EN 13363-1+A1: 2007 | | SOLAR ENERGETIC PROPERTIES | | | | | | | | | | | | | | VISUAL PROPERTIES | |
|---|------------------------------|----------------------------|------|-------------------------|--------------------------|----------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|--|-----|-------------------|--|
| | | FABRIC | | FABRIC + GLAZING | | | | | | | | | | G-factor = total solar energy transmittance | | | |
| | | | | EXTERIOR | | | | | INTERIOR | | | | | | | | |
| | | | | As = Solar Absorbance % | Rs = Solar Reflectance % | Ts = Solar Transmittance % | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | | | | |
| references | colours | front | back | | | | | | | | | | | | | | |
| 001045 | coconut | front | 78,3 | 14,4 | 7,3 | 0,23 | 0,18 | 0,12 | 0,10 | 0,64 | 0,62 | 0,52 | 0,30 | 7,1 | 7,0 | | |
| | | back | 77,5 | 15,2 | 7,3 | 0,23 | 0,18 | 0,12 | 0,10 | 0,64 | 0,62 | 0,52 | 0,30 | 7,1 | 7,0 | | |
| 008015 | linen lichen | front | 70,6 | 21,1 | 8,3 | 0,23 | 0,18 | 0,12 | 0,09 | 0,60 | 0,59 | 0,50 | 0,29 | 7,8 | 3,9 | | |
| | | back | 59,7 | 32,0 | 8,3 | 0,20 | 0,16 | 0,11 | 0,09 | 0,54 | 0,54 | 0,47 | 0,28 | 7,8 | 3,9 | | |
| 008001 | safari | front | 61,5 | 29,8 | 8,7 | 0,21 | 0,17 | 0,11 | 0,09 | 0,55 | 0,55 | 0,47 | 0,28 | 7,9 | 6,4 | | |
| | | back | 53,0 | 38,3 | 8,7 | 0,21 | 0,17 | 0,11 | 0,09 | 0,55 | 0,55 | 0,47 | 0,28 | 7,9 | 6,4 | | |
| 001074 | grey yellow-green | front | 67,8 | 29,2 | 3,0 | 0,17 | 0,13 | 0,08 | 0,07 | 0,55 | 0,55 | 0,47 | 0,28 | 2,7 | 2,3 | | |
| | | back | 74,4 | 22,6 | 3,0 | 0,18 | 0,14 | 0,09 | 0,07 | 0,58 | 0,58 | 0,49 | 0,29 | 2,7 | 2,3 | | |
| 001012 | grey green | front | 70,1 | 23,5 | 6,5 | 0,21 | 0,16 | 0,10 | 0,09 | 0,58 | 0,58 | 0,49 | 0,29 | 6,0 | 5,4 | | |
| | | back | 73,7 | 19,9 | 6,5 | 0,22 | 0,17 | 0,11 | 0,09 | 0,60 | 0,60 | 0,50 | 0,29 | 6,0 | 5,4 | | |
| 033043 | moss | front | 75,4 | 18,2 | 6,4 | 0,22 | 0,17 | 0,11 | 0,09 | 0,61 | 0,60 | 0,51 | 0,29 | 6,0 | 5,8 | | |
| | | back | 75,2 | 18,4 | 6,4 | 0,22 | 0,17 | 0,11 | 0,09 | 0,61 | 0,60 | 0,51 | 0,29 | 6,0 | 5,8 | | |
| 001044 | palm | front | 80,3 | 12,6 | 7,1 | 0,23 | 0,18 | 0,12 | 0,10 | 0,65 | 0,63 | 0,53 | 0,30 | 7,0 | 6,9 | | |
| | | back | 78,5 | 14,4 | 7,1 | 0,23 | 0,18 | 0,12 | 0,10 | 0,65 | 0,63 | 0,53 | 0,30 | 7,0 | 6,9 | | |
| 001014 | grey turquoise | front | 63,8 | 28,9 | 7,3 | 0,20 | 0,16 | 0,10 | 0,08 | 0,55 | 0,55 | 0,47 | 0,28 | 6,3 | 6,0 | | |
| | | back | 68,8 | 23,8 | 7,3 | 0,21 | 0,17 | 0,11 | 0,09 | 0,58 | 0,58 | 0,49 | 0,29 | 6,3 | 6,0 | | |
| 007009 | pearl grey blue azure | front | 61,5 | 31,0 | 7,5 | 0,20 | 0,16 | 0,10 | 0,08 | 0,54 | 0,54 | 0,47 | 0,28 | 4,4 | 3,4 | | |
| | | back | 57,3 | 35,2 | 7,5 | 0,19 | 0,15 | 0,10 | 0,08 | 0,52 | 0,52 | 0,45 | 0,28 | 4,4 | 3,4 | | |
| 001070 | grey pearl grey-blue azure | front | 73,4 | 23,0 | 3,6 | 0,19 | 0,14 | 0,09 | 0,08 | 0,58 | 0,58 | 0,49 | 0,29 | 3,0 | 2,9 | | |
| | | back | 76,5 | 19,8 | 3,6 | 0,20 | 0,15 | 0,09 | 0,08 | 0,60 | 0,59 | 0,50 | 0,29 | 3,0 | 2,9 | | |

Solar energetic properties

| Serge 600 European Standard EN 14501 Calculation G-value according to EN 13363-1+A1: 2007 | | SOLAR ENERGETIC PROPERTIES | | | | | | | | | | | | | | VISUAL PROPERTIES | |
|---|-------------------------|----------------------------|------|-------------------------|--------------------------|----------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|---------------------------------|--|-----|-------------------|--|
| | | FABRIC | | FABRIC + GLAZING | | | | | | | | | | G-factor = total solar energy transmittance | | | |
| | | | | EXTERIOR | | | | | INTERIOR | | | | | | | | |
| | | | | As = Solar Absorbance % | Rs = Solar Reflectance % | Ts = Solar Transmittance % | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | Glazing D - Gv = 0,32 - U = 1,1 | Glazing A - Gv = 0,85 - U = 5,8 | Glazing B - Gv = 0,76 - U = 2,9 | Glazing C - Gv = 0,59 - U = 1,2 | | | | |
| references | colours | front | back | | | | | | | | | | | | | | |
| 001009 | grey blue azure | front | 76,0 | 18,4 | 5,6 | 0,21 | 0,16 | 0,10 | 0,09 | 0,61 | 0,60 | 0,51 | 0,29 | 4,7 | 4,6 | | |
| | | back | 77,6 | 16,8 | 5,6 | 0,22 | 0,17 | 0,11 | 0,09 | 0,62 | 0,61 | 0,51 | 0,29 | 4,7 | 4,6 | | |
| 001094 | lagoon | front | 78,0 | 15,2 | 6,8 | 0,23 | 0,18 | 0,11 | 0,09 | 0,63 | 0,62 | 0,52 | 0,30 | 6,6 | 6,5 | | |
| | | back | 77,4 | 15,8 | 6,8 | 0,23 | 0,18 | 0,11 | 0,09 | 0,63 | 0,62 | 0,52 | 0,30 | 6,6 | 6,5 | | |
| 001042 | shade | front | 75,8 | 16,7 | 7,5 | 0,23 | 0,18 | 0,12 | 0,10 | 0,62 | 0,61 | 0,51 | 0,29 | 7,4 | 7,2 | | |
| | | back | 76,0 | 16,5 | 7,5 | 0,23 | 0,18 | 0,12 | 0,10 | 0,62 | 0,61 | 0,51 | 0,29 | 7,4 | 7,2 | | |
| 001001 | grey grey | front | 81,3 | 15,1 | 3,5 | 0,20 | 0,16 | 0,10 | 0,08 | 0,63 | 0,62 | 0,52 | 0,30 | 3,6 | 3,5 | | |
| | | back | 81,4 | 15,1 | 3,5 | 0,20 | 0,16 | 0,10 | 0,08 | 0,63 | 0,62 | 0,50 | 0,30 | 3,6 | 3,5 | | |
| 001061 | grey white-pearl grey | front | 63,0 | 33,2 | 3,9 | 0,17 | 0,13 | 0,08 | 0,07 | 0,52 | 0,53 | 0,46 | 0,28 | 3,6 | 3,0 | | |
| | | back | 70,9 | 25,2 | 3,9 | 0,19 | 0,14 | 0,09 | 0,08 | 0,57 | 0,57 | 0,49 | 0,29 | 3,6 | 3,0 | | |
| 001010 | grey charcoal | front | 86,5 | 9,9 | 3,6 | 0,22 | 0,16 | 0,10 | 0,09 | 0,66 | 0,64 | 0,54 | 0,30 | 3,6 | 3,4 | | |
| | | back | 83,8 | 12,6 | 3,6 | 0,21 | 0,16 | 0,10 | 0,08 | 0,64 | 0,63 | 0,53 | 0,30 | 3,6 | 3,4 | | |
| 010010 | charcoal charcoal | front | 91,4 | 5,0 | 3,6 | 0,23 | 0,17 | 0,10 | 0,09 | 0,69 | 0,67 | 0,55 | 0,30 | 3,6 | 3,6 | | |
| | | back | 91,6 | 4,8 | 3,6 | 0,23 | 0,17 | 0,10 | 0,09 | 0,69 | 0,67 | 0,55 | 0,30 | 3,6 | 3,6 | | |
| 030030 | pure black pure black | front | 90,4 | 3,7 | 5,9 | 0,18 | 0,14 | 0,09 | 0,07 | 0,64 | 0,64 | 0,54 | 0,30 | 5,9 | 5,9 | | |
| | | back | 90,4 | 3,7 | 5,9 | 0,18 | 0,14 | 0,09 | 0,07 | 0,64 | 0,64 | 0,54 | 0,30 | 5,9 | 5,9 | | |
| 011011 | bronze bronze | front | 88,0 | 8,1 | 3,9 | 0,22 | 0,17 | 0,10 | 0,09 | 0,67 | 0,65 | 0,54 | 0,30 | 3,8 | 3,8 | | |
| | | back | 87,7 | 8,4 | 3,9 | 0,22 | 0,17 | 0,10 | 0,09 | 0,67 | 0,65 | 0,54 | 0,30 | 3,8 | 3,8 | | |
| 010011 | charcoal bronze | front | 87,4 | 6,5 | 6,1 | 0,18 | 0,14 | 0,09 | 0,07 | 0,62 | 0,63 | 0,54 | 0,30 | 6,1 | 6,2 | | |
| | | back | 87,9 | 6,0 | 6,1 | 0,18 | 0,14 | 0,09 | 0,07 | 0,62 | 0,63 | 0,54 | 0,30 | 6,1 | 6,2 | | |


| | |
|--|-----------|
| GLAZING A = clear single glazing 4 mm | Gv = 0,85 |
| GLAZING B = clear double glazing (4/12/4), space filled with air | Gv = 0,76 |
| GLAZING C = double glazing (4/16/4), with a low emissivity coating in position 3, space filled with argon | Gv = 0,59 |
| GLAZING D = reflective double glazing (4/16/4), with a low emissivity coating in position 2, space filled with argon | Gv = 0,32 |

Working of a sunscreen



Sunscreen = protection against sunrays

Sunscreen means protection against the sunrays, so the function is the protection against light and heat, which is expressed in several properties.



| | |
|-----------------|-----------------------------|
| Rs | Solar reflectance |
| As | Solar absorptance |
| Ts | Solar transmittance |
| Te,n-dif | Diffuse solar transmittance |
| Te,n-n | Normal solar transmittance |

Classes indicate effect of a sunscreen


Based on certain properties, the screen can be split up in classes, from 0 to 4. Those classes are used, starting from the norm EN 14501, to indicate the effect of a certain sunscreen.

| influence on thermal and visual comfort | |
|---|--------------------|
| Class 0 | very little effect |
| Class 1 | little effect |
| Class 2 | moderate effect |
| Class 3 | good effect |
| Class 4 | very good effect |

Visual properties

Openness factor

The openness of a screen is indicated by the openness factor = **OF**. The openness coefficient is the relative area of the openings in the fabric seen under a given incidence. The openness factor is seen under a normal incidence.



The sunrays are subdivided in: **Visible light**, **UV-light** and **IR-light**.

Visible light (55% of the sun-energy) is that part for which our eyes are most sensitive. How larger the light intensity, how more detrimental for our eyes.

The factor Visible Light Transmittance = **Tv**, is the ratio of visible light that will be transmitted. How lower this factor can be kept, how better for the eyes.

UV-light (3% of the sun-energy) is the part of radiation which is detrimental for our health. This factor is indicated by the UV Transmittance = **Tuv**. This is the quantity UV-light transmitted by the sunscreen.

IR-light is invisible. This is however 42% of the sun-energy. These rays care for the reheating of solid substances and gases.

Influence of colours

The choice of the colour has direct influence on the criteria which justify the use of sunscreen protection:

- Protection against visible light, expressed by the factor **Tv**.
- Protection against sun-energy, expressed by the **G** value.
- Protection against secondary heat, expressed by the factor **Qi**.
- Protection against UV-light, expressed by the factor **Tuv**.

Visual properties: classes

Glare control

The capacity of the solar protection device to control the luminance level of openings and to reduce the luminance contrasts between different zones within the field.

| Tv,n-n | Tv,n-dif | | | |
|----------------------|-----------------|------------------------|------------------------|-----------------|
| | Tv,n-dif < 0,02 | 0,02 ≤ Tv,n-dif < 0,04 | 0,04 ≤ Tv,n-dif < 0,08 | Tv,n-dif ≥ 0,08 |
| Tv,n-n > 0,10 | 0 | 0 | 0 | 0 |
| 0,05 < Tv,n-n ≤ 0,10 | 1 | 1 | 0 | 0 |
| Tv,n-n ≤ 0,05 | 3 | 2 | 1 | 1 |
| Tv,n-n = 0,00 | 4 | 3 | 2 | 2 |

Privacy at night

Night privacy is the capacity of an internal or external blind or a shutter in the fully extended position or fully extended and closed position to protect persons, at night in normal light conditions from external view. External views means the ability of an external observer located 5m from the fully extended and closed product, to distinguish a person or object standing 1m behind the protection device in the room.

| Tv,n-n | Tv,n-dif | | |
|----------------------|---------------------|------------------------|-----------------|
| | 0 < Tv,n-dif ≤ 0,04 | 0,04 < Tv,n-dif ≤ 0,15 | Tv,n-dif > 0,15 |
| Tv,n-n > 0,10 | 0 | 0 | 0 |
| 0,05 < Tv,n-n ≤ 0,10 | 1 | 1 | 1 |
| Tv,n-n ≤ 0,05 | 2 | 2 | 2 |
| Tv,n-n = 0,00 | 4 | 3 | 2 |

Visual contact with the outside

Visual contact with the outside is the capacity of the solar protection device to allow an exterior view when it is fully extended. This function is affected by different light conditions during the day.

| Tv,n-n | Tv,n-dif | | |
|----------------------|---------------------|------------------------|-----------------|
| | 0 < Tv,n-dif ≤ 0,04 | 0,04 < Tv,n-dif ≤ 0,15 | Tv,n-dif > 0,15 |
| Tv,n-n > 0,10 | 4 | 3 | 2 |
| 0,05 < Tv,n-n ≤ 0,10 | 3 | 2 | 1 |
| Tv,n-n ≤ 0,05 | 2 | 1 | 0 |
| Tv,n-n = 0,00 | 0 | 0 | 0 |

Daylight utilisation

Daylight utilisation is characterised by:

- the capacity of the solar protection device to reduce the time period during the artificial light is required.
- the capacity of the solar protection device to optimise the daylight which is available.

| CLASS | 0 | 1 | 2 | 3 | 4 |
|----------|-----------------|------------------------|------------------------|------------------------|-----------------|
| Tv,dif-h | Tv,dif-h < 0,02 | 0,02 ≤ Tv,dif-h < 0,10 | 0,10 ≤ Tv,dif-h < 0,25 | 0,25 ≤ Tv,dif-h < 0,40 | Tv,dif-h ≥ 0,40 |




Working of a sunscreen




Thermal comfort

Fabric

Energy radiated by the sun, will be split up in 3 factors:

| factor 1: | factor 2: | factor 3: |
|--|---|--|
|  <p>As = Solar absorptance is the ratio of the absorbed flux to the incident flux.</p> |  <p>Rs = Solar reflectance is the fraction of the incident solar radiation that is directly reflected by the component.</p> |  <p>Ts = Solar transmittance is the sum of the (normal) direct solar transmittance and the diffuse solar transmittance. This is the fraction of the total transmitted energy to the total incident solar radiation.</p> |
| These 3 factors together are always 100% | | |

The G-factor



| | |
|-----------|---|
| Rs | Solar reflectance |
| As | Solar absorptance |
| Te | Direct solar transmittance |
| Qi | Secondary heat transfer factor |
| G | G-factor = total solar energy transmittance |

Sunscreens are always used in combination with a glazing. These together will prevent a large quantity of energy, sent by the sun to the earth, which is indicated by the: Total Solar Energy Transmittance, or **G-factor**.

The **G** value is the ratio between the total solar energy transmitted into a room through a window and the incident solar energy on the window. The **G_{tot}** is the solar factor of the combination of glazing and solar protection device.

The **G_v** is the solar factor of the glazing alone. The shading coefficient is defined as the ratio of the solar factor of the combined glazing and solar protection device **G_{tot}** to that of the glazing alone **G_v**.

The total solar energy transmitted through a window consists of two parts:

- 1) Radiation: measured by the solar transmittance: **Te,tot**
- 2) Heat: measured by the secondary heat transfer: **Qi**


$$G = Te,tot + Qi$$

The factor **Te,tot**, is the quantity of energy, which will pass the combination solar protection device and window.

The factor **Qi** is the quantity of heat which is released by the absorption of energy in the sunscreen protection system = combination sunscreen + glazing.

The **G-factor** is the most important factor to explain the efficiency of a combination sunscreen + glazing, as protection against the energy of the sun. The **G-factor** divided into his components explains the difference in efficiency between exterior and interior sunscreen.

$$G = Te,tot + Qi$$



The direct solar transmittance **Te,tot** is the same for interior and exterior use of sunscreens.

The secondary heat factor **Qi** for interior sunscreen is bigger then for exterior sunscreen. For interior use, the heat, produced by the absorption of energy, will be transmitted to the room inside. By exterior use, the heat will be transmitted to the outside, without any inconvenience at the inside.

Also the colour of the sunscreen has an influence on the **G-factor**. Dark colours will absorb a lot of sun energy and will transmit this to heat. If the screen is used for exterior, heat will have no influence inside the room, contrary to a screen used for interior. This is why a darker screen is ideal for exterior use and a lighter screen for interior use.



Thermal comfort: classes

Total Solar energy Transmittance = G-factor

| CLASS | 0 | 1 | 2 | 3 | 4 |
|------------------|-------------------------|--------------------------------|--------------------------------|--------------------------------|-------------------------|
| G _{tot} | G _{tot} ≥ 0,50 | 0,35 ≤ G _{tot} < 0,50 | 0,15 ≤ G _{tot} < 0,35 | 0,10 ≤ G _{tot} < 0,15 | G _{tot} < 0,10 |


Secondary Heat transfer = Qi

| CLASS | 0 | 1 | 2 | 3 | 4 |
|-------|-----------|------------------|------------------|------------------|-----------|
| Qi | Qi ≥ 0,30 | 0,20 ≤ Qi < 0,30 | 0,10 ≤ Qi < 0,20 | 0,03 ≤ Qi < 0,10 | Qi < 0,03 |

Normal Solar transmittance = protection against direct transmission

The ability of a solar protection device to protect persons and surroundings from direct irradiation is measured by the direct/direct solar transmittance of the device in combination with the glazing. **Te,n-n** is used as measure for this property.

reflects sunlight outdoors





Rijksweg 125, 8531 Bavikhove - Belgium · T +32 (0)56 35 35 33 · F +32 (0)56 35 80 48 · www.copaco.be